

Valvoline Performance Products – Tectyl

Version: TE050/05

## Tectyl™ 4D750

**Premium ultra-low VOC containing, hollow section, corrosion preventive compound**

**Tectyl 4D750** is a resin/oil based, light yellow, liquid corrosion preventive compound.

**Tectyl 4D750** is formulated with a minimum of volatile organic components.

**Tectyl 4D750** is designed for industrial application giving good penetration into folds, flanges and cracks, making it very suitable as a corrosion protective for the inside of car doors and other hollow sections of cars and rolling equipment.

**Tectyl 4D750** cures to a light yellow, translucent, semi-soft film.

### Approvals/Performance levels

<p><b>Tectyl 4D750</b></p> <p><b>Accelerated Corrosion tests:</b> @ Average recommended DFT</p> <p><b>Accelerated Corrosion tests:</b> Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS (Q-Panels, Type R, ASTM A1008) <b>At least 15 days</b></p> <p>Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH (Q-Panels, Type R, ASTM A1008) <b>At least 50 days</b></p>
<p><b>Tectyl 4D750</b> meets <b>SFS 4086:2006</b></p>
<p><b>Estimated Protection Period</b></p> <p>Indoor: 36 months</p>
<p>As Tectyl 4D750 is a chemical drying product, the cure time is depending on the application and environmental conditions.</p>

### Applications

#### Surface Preparation

The maximum performance of **Tectyl 4D750** can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. Valvoline recommends a substrate temperature of 10-35 °C at the time of product application.

#### Application

**Tectyl 4D750** is formulated to be used as supplied. Do not thin **Tectyl 4D750**. Valvoline recommends that the ambient and product temperature be 10-35 °C at the time of product application. Do not thin **Tectyl 4D750**. Tectyl 4D750 can be applied by low pressure air spray application. Details on application can be found in the application chart. As **Tectyl 4D750** is a chemical drying product, care should be taken to avoid prolonged contact of the product in the container with air (oxygen) as much as possible. During use this can be achieved by binding the plastic inner liner around the suction tube with a plastic binder. If not in use, keep the container tightly closed.

#### Removal

**Tectyl 4D750** can be removed in the wet phase with Tectyl Biocleaner, Valvoline 150 or low-pressure steam. If dried and cured, the film of **Tectyl 4D750** can be removed with Valvoline 150 or Tectyl Biocleaner.

### Features & Benefits

#### Superior Protection

At the recommended DFT, the product provides extraordinary protection in the hollow sections against corrosion.

#### Efficient

With a DFT of only 50 microns, Tectyl 4D750 is an efficient corrosion protection, protecting a large area with little amount of the product.

### Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit [www.tectyleurope.com](http://www.tectyleurope.com)

### Typical properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl 4D750	
Flash Point, PMCC [°C]	>180
Density @ 20°C [kg/ltr]	0,91
Recommended Dry Film Thickness over metal profile [microns]	50
Theoretical coverage @ recommended DFT [m <sup>2</sup> /ltr]	24,4
Non Volatile [weight %]	98
Viscosity; Brookfield @ 20°C @ 2 RPM [mPa.s] [cP] @ 20 RPM [mPa.s] [cP]	6000 1500
Penetration [mm] (In house test)	40
Dry to touch time @ 20°C [hours]	72
Volatile Organic Compound Content ISO 11890-2 (10.4) [g/ltr]	50

This information only applies to products manufactured in the following location(s):  
Europe

### Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet <http://sds.valvoline.com>

### Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.

### Storage

Tectyl 4D750 should be stored at temperatures between 10-35 °C. Do not freeze Tectyl 4D750. Mild agitation is recommended prior to use. Due to its composition Tectyl 4D750 can be subject to postproduction viscosity changes during storage. Under proper storage conditions Tectyl 4D750 is best before 9 months after production date.

### Caution

Refer to the Safety Data Sheet for additional handling and first aid information.

### Note

The addition of any product over this coating is not possible. The use of any product under this coating is not recommended and could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Performance level section. If a primer, other than a Valvoline recommended product is required, written authorization must be obtained from Valvoline.

Replaces – TE050/04

™ Trademark of Valvoline, registered in various countries © 2022

All statements, information and data presented herein are believed to be accurate and reliable, but are not to be taken as a guarantee, an express warranty, or an implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which Ellis Enterprises B.V. and its affiliates assume legal responsibility.